


PU Casting Foam Resins

WEBAC® 2260/B60



- ▶ WEBAC® 2260 is a PU rigid foam for filling cavities/voids and thermal insulation.


Range of application

- Filling and sealing of cavities/voids and solidification in masonry structures
- Sealing of pipe ducts
- Filling of hollow bricks (e.g. poroton)
- Repair of floating structures (pontoons)


Properties

- Pressure resistant rigid foam, also cures without water
- Thermal insulation effect
- Chlorine- and CFC-free
- Excellent adhesion
- Slow expansion
- Adjustable reaction time (accelerator **WEBAC® B60**)

Examples



Filling of cavities/voids in masonry



Filling of hollow bricks

WEBAC-Chemie GmbH
Fahrenberg 22
22885 Barsbüttel
Germany
Tel. +49 40 67057-0
Fax +49 40 6703227
info@webac.de

www.webac.de

▶ Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
© WEBAC-Chemie GmbH. Version 03/2020/2

PU Casting Foam Resins

WEBAC® 2260/B60

Technical data	Values			
Mixing ratio	1 : 1 parts by volume			
Apparent density	WEBAC. 2260 + 2% B60 + 4% B60	≈ 180 kg/m ³ ≈ 151 kg/m ³ ≈ 43 kg/m ³		
Density, 20 °C / 68 °F (ISO 2811)	Comp. A Comp. B	≈ 1.0 g/cm ³ ≈ 1.2 g/cm ³		
Application temperature Building structure and material	> 5 °C / 41 °F			
Viscosity of mixture	30 °C / 86 °F ≈ 500 mPa·s		23 °C / 73 °F ≈ 600 mPa·s	12 °C / 54 °F ≈ 1,100 mPa·s
	<p>30 °C / 86 °F</p> <p>without B60 ≈ 5 min • ≈ 30 min • ≈ 4-times 2% B60 ≈ 2 min • ≈ 20 min • ≈ 8-times 4% B60 ≈ 1 min 45 s • ≈ 13 min • ≈ 10-times 5% B60 ≈ 1 min 35 s • ≈ 12 min • ≈ 12-times 6% B60 ≈ 1 min 20 s • ≈ 11 min 30 s • ≈ 14-times</p> <p>23 °C / 73 °F</p> <p>without B60 ≈ 5 min • ≈ 50 min • ≈ 4-times 2% B60 ≈ 2 min 30 s • ≈ 20 min • ≈ 8-times 4% B60 ≈ 2 min • ≈ 16 min • ≈ 12-times 5% B60 ≈ 1 min 30 s • ≈ 14 min • ≈ 14-times</p> <p>12 °C / 54 °F</p> <p>without B60 ≈ 15 min • ≈ 2 h • ≈ 4-times 2% B60 ≈ 8 min • ≈ 1.5 h • ≈ 8-times 4% B60 ≈ 4 min • ≈ 75 min • ≈ 10-times 5% B60 ≈ 3 min 30 s • ≈ 55 min • ≈ 12-times 6% B60 ≈ 3 min • ≈ 60 min • ≈ 15-times</p>			
Foam reaction Start • End • Expansion (quantity to be added referring to component A)				
Compressive strength 7 d, 23 °C / 73 °F (DIN 53421)	without B60 2% B60 4% B60	≈ 1.8 N/mm ² ≈ 0.7 N/mm ² ≈ 0.4 N/mm ²		
Thermal insulation value λ _R • layer thickness	without B60 2% B60 4% B60	≈ 0.041 W/mK • ≈ 24 mm ≈ 0.043 W/mK • ≈ 55 mm ≈ 0.042 W/mK • ≈ 57 mm		
GISCODE	PU40			
EPD	EPD-DBC-20130014-IBG1-D			
Exposure scenarios according to REACH	Assessment of industry standard application			

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products. © WEBAC-Chemie GmbH. Version 03/2020/2

PU Casting Foam Resins

WEBAC® 2260/B60



Preparatory work

- ▶ See **WEBAC Brochure Sealing of Masonry**



Sealing of Masonry



Mixing

- Stir component A briefly before use

Casting

- Empty component A and B at the given mixing ratio into a bucket (make sure that the containers are completely empty) and mix homogeneously

Application by 2C pump

- Fill component A and B into the respective hoppers
- The components are mixed homogeneously in the mixing head

WEBAC® B60

- Added quantity referring to **component A** according to table ▶ p. 61
- Mix into **component A** immediately before use



Application instruction

- Mixed material is moisture-sensitive; contact with water (e.g. rain) must be avoided
- The mixture must be used completely within the reaction time
- Make sure the filter in the hopper is clean
- Only use pure WEBAC material without any residues of cleaning agents or other impurity

- The reaction speed is influenced by the temperature of the material and the building structure – higher temperatures accelerate, lower temperatures slow down the reaction



Application

- Fill the mixed material into the pouring hole or using a 2C pump via packers/lances
- In case of higher filling levels the material should be applied layer by layer



Final work and cleaning

- Once the material has cured remove the packers/lances
- Clean and close the drill holes with suitable non-shrinking mortar
- The patching can be removed as soon as the injection process is completed and the filling material is cured
- Clean the pump with **WEBAC® Cleaner A**
- Use **WEBAC® Cleaner B** for dissolving cured material but never for flushing pumps
- Observe the technical data sheets of the injection pump and cleaners used
- For detailed information refer to the operating manual of the injection pump used



Note

Quantity of added accelerator **WEBAC® B60** refers to component A!

WEBAC-Chemie GmbH
Fahrenberg 22
22885 Barsbüttel
Germany
Tel. +49 40 67057-0
Fax +49 40 6703227
info@webac.de

www.webac.de

▶ Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
© WEBAC-Chemie GmbH. Version 03/2020/2

PU Casting Foam Resins

WEBAC® 2260/B60

Product data			
Application	<ul style="list-style-type: none"> • Casting • Injection by 2C pump 		
Packing	WEBAC® 2260		WEBAC® B60
	Comp. A	Comp. B	Unit
	9.25 kg	11.25 kg	0.5 kg
	5 kg	6 kg	0.25 kg
Storage	<ul style="list-style-type: none"> • Between 5 °C / 41 °F and 30 °C / 86 °F • Protect from moisture • In original, sealed containers 		
Compatibility/Resistance	<ul style="list-style-type: none"> • Compatible with concrete, steel, foil, cable sheathing and WEBAC injection materials • Resistant to harmful salts, alkalis and acids in common concentrations in building structures 		

WEBAC-Chemie GmbH
 Fahrenberg 22
 22885 Barsbüttel
 Germany
 Tel. +49 40 67057-0
 Fax +49 40 6703227
 info@webac.de

www.webac.de

Test certificates

- Test certificates on request

Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or www.webac-grouts.com.

Waste disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or www.webac-grouts.com and the safety data sheets.

► Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
 © WEBAC-Chemie GmbH. Version 03/2020/2