

# WEBAC® Contact Adhesive



- ▶ WEBAC® Contact Adhesive is used for gluing WEBAC® Polymer Swelling Tape and WEBAC® Bentonite Swelling Tape to the substrate.

## Range of application

- Gluing of **WEBAC® Polymer Swelling Tape** and **WEBAC® Bentonite Swelling Tape**


## Properties

- Flexible
- Fast curing
- Good adhesion also to wet surfaces
- Ready to use

WEBAC-Chemie GmbH  
 Fahrenberg 22  
 22885 Barsbüttel  
 Germany  
 Tel. +49 40 67057-0  
 Fax +49 40 6703227  
 info@webac.de

[www.webac.de](http://www.webac.de)

## Example



## Technical data

	Values	
Density, 23 °C / 73 °F	≈ 1.4 g/cm <sup>3</sup>	
Skin forming time at 50% air moisture	23 °C / 73 °F	≈ 5 min
Curing time, at 3.5 mm layer thickness, at 50% air moisture	23 °C / 73 °F	≈ 24 h
Application temperature	5 °C / 41 °F up to 40 °C / 104 °F	
Tensile strength · elongation at break	≈ 3.0 N/mm <sup>2</sup> · ≈ 300%	
E modulus	≈ 1.6 N/mm <sup>2</sup>	

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

## ▶ Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.  
 © WEBAC-Chemie GmbH. Version 03/2020

Special Construction Products

# WEBAC® Contact Adhesive

Product data	
Application	<ul style="list-style-type: none"> <li>• By cartridge</li> </ul>
Consumption depending on substrate	<ul style="list-style-type: none"> <li>• 3–10 m per cartridge</li> </ul>
Packing	<p><b>Unit</b> 290 ml</p>
Storage	<ul style="list-style-type: none"> <li>• Between 5 °C / 41 °F and 25 °C / 77 °F</li> <li>• Protect from moisture</li> <li>• In original, sealed containers</li> </ul>

WEBAC-Chemie GmbH  
 Fahrenberg 22  
 22885 Barsbüttel  
 Germany  
 Tel. +49 40 67057-0  
 Fax +49 40 6703227  
 info@webac.de

[www.webac.de](http://www.webac.de)

## Test certificate

- National Test Certificate for **WEBAC® Polymer Swelling Tape** and **Bentonite Swelling Tape** in combination with **WEBAC® Contact Adhesive**

## Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or [www.webac-grouts.com](http://www.webac-grouts.com).

## Waste disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or [www.webac-grouts.com](http://www.webac-grouts.com) and the safety data sheets.

## ► Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.  
 © WEBAC-Chemie GmbH. Version 03/2020