

## PU Injection Resins

# WEBAC® PURseal

- ▶ Fast curing, very high (early) strength PU resin which can also be modified into an extremely fast reacting rigid foam by using accelerators and additives

### Range of application

- Permanent sealing
- Securing of foundation pits and tunnel systems
  - Quick stopping of flowing water and durable sealing
  - Stabilization and connection of tubings to rock mass
  - Waterproofing against pressing water in fractured rock and loose ground
  - Underground securing of retaining walls in road construction
  - Consolidation and sealing of flood protection systems, road and railway embankments
- Subsoil and rock mass stabilization
  - Solidification of rock and stabilization of soil
  - Reinforcement of foundation
  - Ground consolidation of existing buildings
  - Lifting of concrete slabs
  - Slope stabilization
- Anchor bonding


WEBAC-Chemie GmbH  
 Fahrenberg 22  
 22885 Barsbüttel  
 Germany  
 Tel. +49 40 67057-0  
 Fax +49 40 6703227  
 info@webac.de  
 www.webac-grouts.com

[www.webac.de](http://www.webac.de)


### Properties

- Cures without water contact to form a pore-free, compact and high strength material
- Slight foam formation upon contact with water
- Fast curing – permanent sealing
- Environmentally sound
- Reaction time and foaming activity adjustable  
 (WEBAC® PURseal M ACC3 and WEBAC® PURseal M SF)

### Examples



Consolidation and sealing



Consolidation and sealing of a bored pile wall

## Technische Information Technical Information

## PU Injection Resins

# WEBAC® PURseal

Technical data	Values
Mixing ratio	1 : 1 parts by volume
Density 23 °C/73 °F (ISO 2811)	Comp. A ≈ 1.01 g/cm <sup>3</sup> Comp. B ≈ 1.23 g/cm <sup>3</sup>
Viscosity, 23 °C/73 °F (ISO 3219)	Comp. A ≈ 300 mPa•s Comp. B ≈ 260 mPa•s
Reaction time Flow limit   solid	23 °C/73 °F ≈ 40 s   ≈ 60 s
Compressive strength uniaxial, 3 d, 21 °C/70 °F (ISO 604)	≈ 80 MPa (N/mm <sup>2</sup> )
Shore hardness D 3 d, 21 °C/70 °F (ISO 868)	≈ 73/65
Flashpoint (ISO 2719)	Comp. A > 140 °C/284 °F Comp. B > 250 °C/482 °F
GISCODE	PU40
EPD	EPD-DBC-20130014-IBG1-DE
Exposure scenarios according to REACH	Assessment of industry standard application

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

WEBAC-Chemie GmbH  
Fahrenberg 22  
22885 Barsbüttel  
Germany  
Tel. +49 40 67057-0  
Fax +49 40 6703227  
info@webac.de  
www.webac-grouts.com

[www.webac.de](http://www.webac.de)

## PU Injection Resins

# WEBAC® PURseal



### Mixing

Application by 2C pump

- Fill component A and B into the respective hoppers of **WEBAC IP 2K-F2** or process directly from the containers (**WEBAC IP 2K-40**)
- The components are mixed homogeneously in the mixing head



### Application instruction

- We recommend storing the components at a minimum temperature of 15 °C/59 °F for at least 12 hours prior to use to ensure optimum application performance.
- Protect components from moisture penetration (skin formation, pump-damaging precipitates, foam formation due to moisture)
- Only use pure WEBAC material without any residues of cleaning agents or other impurity
- The reaction speed is influenced by the temperature of the material and the building structure – higher temperatures accelerate, lower temperatures slow down the reaction

Only use injection pumps for one type of material (silicate resin or polyurethane resin). When changing the material, the pump must be cleaned thoroughly and all material and cleaning agent must be removed entirely. For further information, please contact WEBAC.



### Application

- Depending on application

We will be pleased to advise you.  
Please contact us! Phone +49 40 670 57-0



### Cleaning

- When interrupting work for a short period of time the mixing head can be cleaned with component A of the injection material.
- When interrupting work for a longer period of time and after conclusion of the injection process it is necessary to rinse the hoses and the pistons of both components with **WEBAC® Cleaner A**.
- For detailed information refer to the technical data sheet of the cleaner and the operating manual of the injection pump used.

**WEBAC-Chemie GmbH**  
Fahrenberg 22  
22885 Barsbüttel  
Germany  
Tel. +49 40 67057-0  
Fax +49 40 6703227  
info@webac.de  
www.webac-grouts.com

[www.webac.de](http://www.webac.de)

## PU Injection Resins

# WEBAC® PURseal

Product data							
Application	<ul style="list-style-type: none"> <li>Injection with 2C pump (WEBAC® IP 2K-40, WEBAC® IP 2K-F2)</li> <li>Mixing tube, Ø 12 mm, l = 300 mm</li> </ul>						
Packing	<table border="0"> <tr> <td>Comp. A</td> <td>980 kg</td> <td>20.2 kg</td> </tr> <tr> <td>Comp. B</td> <td>1,200 kg</td> <td>24.8 kg</td> </tr> </table>	Comp. A	980 kg	20.2 kg	Comp. B	1,200 kg	24.8 kg
Comp. A	980 kg	20.2 kg					
Comp. B	1,200 kg	24.8 kg					
Storage	<ul style="list-style-type: none"> <li>Between 5 °C/41 °F and 30 °C/86°F</li> <li>Protect from moisture</li> <li>In original, sealed containers</li> </ul>						



### Test certificates

- Test certificate (for drinking water) according to KTW recommendations (German Federal Health Gazette): B (repair system for containers)
- Test certificate (for drinking water) according to KTW recommendations (German Federal Health Gazette): C (equipment gear)
- Assessment and effects of construction products on soil and ground water according to DIBt code of practice



### Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or [www.webac-grouts.com](http://www.webac-grouts.com).



### Waste Disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or [www.webac-grouts.com](http://www.webac-grouts.com) and the safety data sheets.

WEBAC-Chemie GmbH  
 Fahrenberg 22  
 22885 Barsbüttel  
 Germany  
 Tel. +49 40 67057-0  
 Fax +49 40 6703227  
 info@webac.de  
[www.webac-grouts.com](http://www.webac-grouts.com)

[www.webac.de](http://www.webac.de)