PU Injection Resins WEBAC® PURseal M S



Range of Application	 Subsoil and rock mass stabilization Solidification of rock and stabilization of soil Reinforcement of foundation Ground consolidation of existing buildings Lifting of concrete slaps Slope stabilization 	
	 Securing of foundation pits and tunnel systems Quick stopping of flowing water and durable sealing Stabilization and connection of tubbings to rock mass Waterproofing against pressing water in fractured rock and loose ground Underground securing of retaining walls in road construction Consolidation and sealing of flood protection systems, road and railway embankments Anchor bonding 	WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de
Properties	 Polyurethan-based injection resin Cures without water contact to form a compact and high strength material Slight foam formation upon contact with water Fast curing – permanent sealing 	www.webac.de
	 Reaction time and foaming activity adjustable (WEBAC: PURseal M ACC3 and WEBAC: PURseal M SF) 	
Test Certificates	 National Technical Approval for curtain injection in contact with soil and groundwater Test certificate according to KTW recommendations: C (equipment gear) Environmental Product Declaration (EPD) 	

Examples





Consolidation and sealing

Subsoil stabilization

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products. © WEBAC-Chemie GmbH. Version 01/2025

PU Injection Resins WEBAC_® PURseal M S

PU Injection Resins WEBAC® PUR	seal M	S	
Technical Data			
Mixing ratio		1 : 1 parts by volume	
Density, 23 °C (DIN ISO 2811)	Comp. A Comp. B	≈ 1.01 g/cm³ ≈ 1.23 g/cm³	
Viscosity, 23 °C (DIN ISO 3219)	Comp. A Comp. B	≈ 400 mPa·s ≈ 260 mPa·s	
Reaction time Flow limit • Solid		23 °C ≈ 60 s to ≈ 10 min • ≈ 90 s to ≈ 30 min (depending on adjustment)	WEBAC-Chemie GmbH
Compressive strength uniaxial, 3 d, 21 °C (DIN ISO 604)	≈ 60 MPa (N/mm²)		Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227
Shore hardness D, 3 d, 21 °C (DIN ISO 868)	≈ 70/65		info@webac.de www.webac.de
Flashpoint (DIN ISO 2719)	Comp. A Comp. B	> 140 °C > 250 °C	
GISCODE		PU40	
EPD			
Exposure scenarios according to REACH			

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory An the data indicated in this technical data sheet and any related inholded by binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products. © WEBAC-Chemie GmbH. Version 01/2025

PU Injection Resins WEBAC[®] PURseal M S

Preparatory Work

- Check the injectability of the rock, subsoil or building structure
- Determine a remediation concept in accordance with the applicable rules and standards
- Carrying out a test injection if necessary

Application Instruction

- Injection by 2C pump
- We recommend storing the components at a minimum temperature of 15 °C for at least 12 hours prior to use to ensure optimum application performance
- Protect components from moisture penetration (skin formation, pump-damaging precipitates, foam formation due to moisture)
- Only use pure WEBAC material without any residues of cleaning agents or other impurity
- The reaction speed is influenced by the temperature of the material and the building structure – higher temperatures accelerate, lower temperatures slow down the reaction

Only use injection pumps for one type of material (silicate resin or polyurethane resin). When changing the material, the pump must be cleaned thoroughly and all material and cleaning agent must be removed entirely. For further information, please contact WEBAC.

Mixing

- Fill component A and B into the respective hoppers of WEBAC. IP 2K-PU or process directly from the containers (WEBAC. IP 2K-40)
- Components are mixed by a static mixer in the mixing head

Application

Depending on application
 We will be pleased to advise you.
 Please contact us! Phone +49 40 670 57-0

Cleaning

- When interrupting work for a short period of time the mixing head can be cleaned with component A of the injection material
- When interrupting work for a longer period of time and after conclusion of the injection process it is necessary to rinse the hoses and the pistons of both components with WEBAC. Cleaner A
- Observe the technical data sheet of the injection pump and cleaners used
- For detailed information refer to the operating manual of the injection pump

WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de

www.webac.de

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products. © WEBAC-Chemie GmbH. Version 01/2025

PU Injection Resins WEBAC® PURseal M S

P	ro	d	u	C	t	D	а	t	а

Delivery form	<mark>Comp. A</mark> 20.5 kg	Comp. B 24.8 kg		
	 Between 5 °C and 30 °C 			
Storage	Protected from moisture			
	 In original, sealed containers 			

Occupational Safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or www.webac-grouts.com.

Waste Disposal

In Germany, empty containers can be disposed of via "Interzero Circular Solutions Germany GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Disposal Notes" in our product catalog or www.webac-grouts.com and the safety data sheets.



WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de

www.webac.de

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products. © WEBAC-Chemie GmbH. Version 01/2025