Injection Pumps

WEBAC_® IP 1K-F3 C€

▶ WEBAC_® IP 1K-F3 is a compressed air-operated 1C high-pressure piston pump specially designed for injection resins with short pot life and high viscosity.

Range of application


- · Crack injection
- Post-construction damp proof course (dpc)
- Injection of injection tube
- Surface injection/sealing
- Sewer repair

Suitable for

- PU injection foam resins
- PU combi injection resins
- PU injection resins
- Epoxy injection resins

Properties

- · Robust design, suitable for construction sites
- Low weight
- Continuously variable pressure regulation
- No heating of material
- Easy to clean and maintain



WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de


www.webac.de

NEBAC

Injection Pumps

WEBAC_® IP 1K-F3 C€

Design of pump



WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de

www.webac.de

Injection Pumps

WEBAC_® IP 1K-F3 C€

Technical data	Values					
Pressure ratio	33 : 1					
Max. delivery rate at free flow	≈ 3 l/min					
Delivery rate per stroke	≈ 14 cm³					
Max. inlet pressure/ safety valve	8 bar					
Max. allowed working pressure	264 bar					
Air requirement	≈ 200 l/min					
Max. material temperature	80 °C / 176 °F					
Dimensions (LxWxH)	≈ 70.5 x 50 x 34 cm					
Weight	≈ 13 kg					



WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67057-0 Fax +49 40 6703227 info@webac.de

www.webac.de

Operation

For the operation of the injection pump, see the pump manual.

Cleaning

- Clean the injection pump with WEBAC. Cleaner A
- Observe the technical data sheet of the cleaners used
- For detailed information refer to the operating manual of the injection pump

Storage

- Always store the injection pump in an upright position
- Fill the cleaned pump system with (water-free) hydraulic oil in case of long non-operating periods

Injection Pumps

WEBAC_® IP 1K-F3 C€

Overview: Range of application

		Sealing of Masonry	Gel Injection (Curtain Injection)	Stabilization of Structures	Crack Repair	Sealing of Joints	Monument Conservation	Sealing of Foundation Pits	Sewer Repair	Soil Solidification
1C pumps	WEBAC _® IP EasyPro	✓		✓	✓	✓	✓	√	✓	✓
	WEBAC _® IP 1K-F4	✓		✓	✓	✓	✓		✓	✓
	WEBAC _® IP 1K-F3	✓		✓	✓	✓	✓		✓	√
	WEBAC _® HP 100	✓		✓	✓		✓			
	WEBAC _® HP 250	✓		✓	✓		✓			
	WEBAC _® HEP 1001	✓		✓	✓		✓			
2C pumps	WEBAC _® IP 2K-F1	✓	✓			✓		✓	✓	√
	WEBAC _® IP 2K-F2	✓		√			√	✓	✓	√
	WEBAC。 IP GelCompact	✓	✓			√		✓	✓	√
	WEBAC _® HP 50 2K	✓		✓		✓	✓			

WEBAC-Chemie GmbH Fahrenberg 22 22885 Barsbüttel Germany Tel. +49 40 67037-0 Fax +49 40 6703227 info@webac.de

www.webac.de

Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or www.webacgrouts.com.

Waste disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or www.webac-grouts.com and the safety data sheets.